

Technical Data Sheet


CHARACTERISTICS

Methylol type, reactive, n-butylated melamine-formaldehyde resin

FORM OF DELIVERY

64% in n-Butanol/Xylene (65/35)

STRUCTURE



SPECIFICATION

Determined per batch

Property

Viscosity DIN EN ISO3219-B

Gardner-Holdt 25°C
(435-1200-3)

L - R

Non-Volatile Matter / Solids

15min at 147°C
(435-1200-2)

[%]

62-66

Solvent Tolerance (ASTM-Amine)

(435-1200-25-1)

[g/ml]

15 min.

Color, APHA

(435-1019)

30 max.

Haze, APHA

(435-1019)

5 max.

Density (Liquids)

(435-1200-30) at 25°C

LB./Gal.

8.4-8.7

Formaldehyde Content (Sulfite)

(435-1205)

[%]

2.0 max.

Not continually determined

Flash Point (Pensky Martens, closed cup)

analog, DIN EN 22719

[°F]

71
(22°C)

USES :

General purpose baking enamels.

STORAGE STABILITY:

At temperatures up to 25°C the storage stability of Resimene 891 packed in original containers amounts to at least 24 months. Some turbidity may occur in isolated cases but this has no effect on product quality.



Data contained in this publication are based on careful investigations and are intended for information only. Any user is obliged to carry out tests under his own responsibility as to suitability of the product for a particular use and to investigate the possible violation of industrial property rights of third parties. Information is therefore not binding and cannot be construed as guaranteeing specific properties of products as established by law. Any liability as to the exactness and completeness of data is thus excluded. We apply our General Sales Conditions.

INEOS Melamines

	World Area		Customer Order	Technical Support
INEOS Melamines, Inc. 1395 S. Marietta Parkway Bldg. 500, Suite 210 Marietta, GA 30067	North America	☎ ☐	+1 888 723 2873 +1 770 528 6693	+1 413 730 2757 +1 413 730 3444
	South America	☎ ☐	+1 678 999 3172 +1 770 528 6693	+1 413 730 2757 +1 413 730 3444
	Europe-Africa	☎ ☐	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
	Asia Pacific	☎ ☐	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
INEOS Melamines GmbH Alt Fechenheim 34 D 60386 Frankfurt, Germany www.ineosmelamines.com				

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines Inc. (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Ineos Melamines Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines Inc.