

**Technical data sheet**

---

**CHARACTERISTICS**

Hardener active substance approx. 70 %

**FORM OF DELIVERY (f.o.d)**

Low viscosity liquid.

---

**SPECIFICATION****Determined per batch:****Appearance**

clear,  
yellowish  
solution

**pH-Value**

20°C (DIN 19260-63)

6,3-7,0

**Density**

20°C (DIN 12791/1+3)

[g/ml] 1,185-1,195

**Refractive index**

$n_D$   
23°C DIN 51423/2

1,465-  
1,475

**PROPERTIES AND USES**

For use together with aqueous amino-resins, preferably melamine formaldehyde resins.

It is best to add Hypersal XW 335 to the ready prepared resin solution at 20-30 °C, thorough, uniform mixing is important. Generally about 0.1 - 1.2 %. Hypersal XW 335 is added based on resin solids.

**STORAGE**

When Hypersal XW 335 is stored as supplied in undamaged containers, it keeps for at least 12 months without change in technical properties.

# INEOS Melamines

## INEOS Melamines, Inc.

1395 S. Marietta Parkway  
Bldg. 500, Suite 210  
Marietta, GA 30067

## INEOS Melamines GmbH

Alt Fechenheim 34  
D 60386 Frankfurt, Germany

[www.ineosmelamines.com](http://www.ineosmelamines.com)

### World Area

### Customer Order

### Technical Support

North America



+1888 723 2873  
+1770 528 6693

+1413 730 2757  
+1413 730 3444

South America



+1678 999 3172  
+1770 528 6693

+1413 730 2757  
+1413 730 3444

Europe-Africa



+49 (0) 69 4109 2319  
+49 (0) 69 4109 2552

+49 (0) 69 4109 2310  
+49 (0) 69 4109 2628

Asia Pacific



+49 (0) 69 4109 2319  
+49 (0) 69 4109 2552

+49 (0) 69 4109 2310  
+49 (0) 69 4109 2628

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines Inc. (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines Inc. be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any product, process, equipment or formulation in conflict with any patent, and Ineos Melamines Inc. makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED, OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines Inc.