

CHARACTERISTICS

Flow agent (without silicone)

FORM OF DELIVERY (f.o.d)

low viscous liquid

SPECIFICATION

Determined per batch:

Properties**Viscosity EN ISO 3219-B**approx. (2000 s⁻¹; 23°C) [mPas] 17**Iodine Colour Number DIN 6162**

iodine colour number mg l / 100 ml < 2

Non-Volatile Matter

DIN EN ISO 3251 [%] 20-23

Not continually determined: :

Density (Liquids) DIN 12791 p1+3density ca. (20°C) [g / cm³:] 0,91**Flash Point**

(5 to 65°C) DIN 53213 T1 [°C] > 21

USES:

Hypersal XL 460/21LG is a levelling agent which is mainly used within alkyd/melamine resin stoving enamel-paints.

Due to its capacity to improve the surface quality of a crosslinked film, the use of the additive is also usable in other stoving enamel paints such as acrylic/melamine- and polyester/melamine systems, but the suitability has to be tested.

PROCESSING:

Quantity to be added: 1.0 - 2.0 % on paint.

STORAGE:

At temperatures up to 25°C storage stability of Hypersal XL 460/21LG packed in original containers amounts to at least 12 months from the day of production.



	World Area		Customer Support	Technical Support
INEOS Melamines, LLC 730B Worcester Street Springfield, MA 01151	North America		+1 888 723 2873	+1 413 730 2499
	South America		+1 413 730 3814	+1 413 730 2499
	North & South America		+1 413 730 3815 +1 413 730 3817	+1 413 730 2268
INEOS Melamines GmbH Alt Fechenheim 34 D 60386 Frankfurt, Germany	Europa Middle East / Africa	 	+49 (0) 69 4109 2319 +49 (0) 69 4109 2552	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
	Asia / Pacific	 	+86-21-6103 5220 +86-21-6226 5072	+49 (0) 69 4109 2310 +49 (0) 69 4109 2628
www.ineosmelamines.com				

NOTICE: Although the information and recommendations set forth herein (hereinafter "Information") are presented in good faith and believed to be correct as of the date hereof, Ineos Melamines (and its subsidiaries) makes no representations or warranties as to the completeness or accuracy thereof. Information is supplied upon the condition that the persons receiving same will make their own determination as to the suitability for their purpose prior to use. In no event will Ineos Melamines be responsible for damages of any nature whatsoever resulting from the use of or reliance upon Information or the product to which Information refers. Nothing contained herein is to be construed as a recommendation to use any information, product, process, equipment or formulation in conflict with any trademark, copyright, patent or other intellectual property right and Ineos Melamines makes no representation or warranty, express or implied, that the use thereof will not infringe any patent. Certain products may not be regulated or available in some world areas. NO REPRESENTATIONS OR WARRANTIES, EITHER EXPRESS OR IMPLIED INCLUDING WITHOUT LIMITATION ANY IMPLIED WARRANTIES OF MERCHANTABILITY, FITNESS FOR A PARTICULAR PURPOSE OR OF ANY OTHER NATURE ARE MADE HEREUNDER WITH RESPECT TO INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS. Where indicated, ® is a Registered Trademark of Ineos Melamines.